

CORRECT REISSUE

HELLENIC REPUBLIC
MINISTRY OF ECONOMY AND FINANCE
GENERAL STATE CHEMICAL LABORATORY
4th CHEMICAL SERVICE OF ATHENS
4th DEPARTMENT
16, Tsocha Street, Postal Code 11521 Athens
Enquiries: I. Ierapetritis
Fax: 210 6465123 Tel. No.: 210 6479335

Athens, 6.12.2005

Ref. No. 02619/015/000

TO: NEOTEX S.A.
45 Victor Hugo Street,
Postal Code 19437 Athens

SUBJECT: Results of the examination of a sample of
“NEOPOX W”

RE: Your application dated 21.7.2005

In reply to your above referenced application, enclosed please find the report of the examination of the “NEOPOX W” sample that you forwarded to us.

The Head of the Chemical Service

E. Karageorgi

True photocopy, attested by Leonidas Antonopoulos – General State Chemical Laboratory (Signed-Sealed)

ΕΛΛΗΝΙΚΗ ΔΗΜΟΚΡΑΤΙΑ, ΥΠΟΥΡΓΕΙΟ ΕΞΩΤΕΡΙΚΩΝ
ΜΕΤΑΦΡΑΣΤΙΚΗ ΥΠΗΡΕΣΙΑ

RÉPUBLIQUE HELLÉNIQUE, MINISTÈRE DES AFFAIRES ÉTRANGÈRES
SERVICE DES TRADUCTIONS

HELLENIC REPUBLIC, MINISTRY OF FOREIGN AFFAIRS
TRANSLATIONS SERVICE



CORRECT REISSUE

HELLENIC REPUBLIC
MINISTRY OF ECONOMY AND FINANCE
GENERAL STATE CHEMICAL LABORATORY
4th CHEMICAL SERVICE OF ATHENS
4th DEPARTMENT

16, An. Tsocha Street, Postal Code 11521 Athens

Enquiries: Ioannis Ierapetritis

Fax: 210 6469755 Tel. No.: 210 6479000

Athens, 16.11.2005

Ref. No. 02619/015/000

Sample No. 015/050/259/2005

SAMPLE EXAMINATION REPORT

Forwarding Organisation: NEOTEX S.A.
Incoming Document Type-Date: Application, 21.7.2005
Sampling Organisation: NEOTEX S.A.
45 Victor Hugo Street
Postal Code 10437 Athens
Type of Specimen: NEOPOX W Coating material
Sampling Date: 20.7.2005
Sample Name: SAMPLE A
Sample received on: 21.7.2005
Examination Date: From 28.7.2005 to 8.11.2005
Package: To be filled in by the Laboratory

ΕΛΛΗΝΙΚΗ ΔΗΜΟΚΡΑΤΙΑ, ΥΠΟΥΡΓΕΙΟ ΕΞΩΤΕΡΙΚΩΝ
ΜΕΤΑΦΡΑΣΤΙΚΗ ΥΠΗΡΕΣΙΑ

RÉPUBLIQUE HELLÉNIQUE, MINISTÈRE DES AFFAIRES ÉTRANGÈRES
SERVICE DES TRADUCTIONS

HELLENIC REPUBLIC, MINISTRY OF FOREIGN AFFAIRS
TRANSLATIONS SERVICE

RESULTS OF THE EXAMINATION OF THE SAMPLE
SUBMITTED

EXAMINATION TYPE	EXAMINATION METHOD	RESULT
Polymer Identification	FT-IR	Epoxy resin of the Bisphenol-A/ Epichlorohydrin type
Organoleptic examination	In-house	Three successive tests (3d/23oC) with a new aqueous simulant each time: 1 st , 2 nd , 3 rd test: No varying organoleptic characteristics are observed compared to the control.
Overall migration in water with a standard cell	OM1/EN 1186-5 weighted	Three successive tests (3d/23oC) with a new aqueous simulant each time: 1 st : 2.3mg/dm ² , 2 nd : 1.2mg/dm ² 3 rd : <0.5mg/dm ²
Overall migration in isooctane 2d/20oC with a standard cell	OM7/EN 1186-5, modified weighted *	<0.5mg/dm ²
Specific migration of BADGE	EM8 HPLC	A) Water: 1 st cycle: BADGE(OH) ₂ <LOQ (LOQ/water=0.05mg/kg) 2 nd cycle: BADGE(OH) (Cl)=0.013mg/kg. BADGE(OH) ₂ <LOQ 3 rd cycle: BADGE(OH) (Cl)=0.013mg/kg, BADGE(OH) ₂ <LOQ B) Sunflower oil/10days/

ΕΛΛΗΝΙΚΗ ΔΗΜΟΚΡΑΤΙΑ, ΥΠΟΥΡΓΕΙΟ ΕΞΩΤΕΡΙΚΩΝ
ΜΕΤΑΦΡΑΣΤΙΚΗ ΥΠΗΡΕΣΙΑ

RÉPUBLIQUE HELLÉNIQUE, MINISTÈRE DES AFFAIRES ÉTRANGÈRES
SERVICE DES TRADUCTIONS

HELLENIC REPUBLIC, MINISTRY OF FOREIGN AFFAIRS
TRANSLATIONS SERVICE

